U. S. DEPARTMENT OF COMMERCE WASHINGTON 25, D. C.

NATIONAL BUREAU OF STANDARDS PROVISIONAL CERTIFICATE OF ANALYSIS HIGH-TEMPERATURE ALLOY STANDARDS

FOR OPTICAL EMISSION AND X-RAY SPECTROSCOPIC ANALYSES

| NBS No .a/ | 1190 | 1203 | 1204 | 1205 |
|-------------|-----------------------|------------|------------|------------|
| Designation | Udimet 500 | Inco 713-A | Inco 713-B | Inco 713-C |
| Element b/ | | Percent | | |
| С | (0.10) ^c / | (0.01) | (0.03) | (0.19) |
| Mn | .61 | .31 | .41 | .29 |
| Si | .22 | .86 | .56 | .63 |
| Ču | .093 | .19 | .12 | .056 |
| Ni | 51.9 | 75.5 | 70.6 | 67.5 |
| Co | 19.1 | | ~ ~ ~ | |
| Fe | (0.6) | (1.4) | (3.1) | (1.55) |
| Cr | 17.00 | 11.90 | 12.75 | 13.82 |
| Мо | 3.80 | 3.01 | 4.28 | 5.75 |
| W | 80.0 | <0.01 | 0.028 | 0.019 |
| Al | 2.83 | 4.34 | 5.60 | 6.68 |
| Ti | 3.57 | 1.09 | 0.63 | 0.36 |
| Zr | 0.11 | 0.055 | .12 | .46 |
| Nb (Cb) | <0.01 | 1.00 | 1.31 | 1.95 |
| Та | < .01 | 0.34 | 0.46 | 0.67 |

- a/ Size and metallurgical condition: Samples are approximately 1 1/4 in. square and 3/4 in. thick; they were chill cast by a rapid unidirectional solidification technique.
- b/ The standards also contain the elements boron, phosphorous, and sulfur which are expected to be certified at a later date.
- <u>c</u>/ Values in parenthesis are <u>not</u> certified, but are given for additional information on the composition.

The material for each standard was vacuum melted and cast at Allvac Metals Company, Monroe, N. C. Approximately 200-pound heats were melted in a high-frequency induction furnace and individual samples were chill cast simultaneously in a stack mold containing plates of steel onto which the molten metal solidified unidirectionally. The samples were finished by sand blasting the sides and machine grinding the top and bottom. The samples have been marked by NBS numbers on the top, opposite the chill-cast or test surface. (A serial number appears on one side near the top of the sample.)

The homogeneity of the standard samples was investigated by metallographic studies, by optical and x-ray spectroscopic analysis, and by chemical analysis at the National Bureau of Standards.

Chemical analyses were made by: R. K. Bell, E. E. Maczkowske, and E. R. Deardorff, Standard Reference Materials Section, National Bureau of Standards; A. L. Sloan, The Carpenter Steel Co., Reading, Pa.; A. D. Middletown, The International Nickel Co., Huntington Alloy Works, Huntington, W. Va.; S. Kallman, H. Oberthin, and J. Oberthin, Ledoux and Co., Teaneck, N. J.; and L. M. Melnick, U. S. Steel Corp., Monroeville, Pa.

(OVER)